

TECHNICAL DATA SHEET

Crosslinkable Polyethylene Compound

XLPE – LS124NTA

CHEMTECH XLPE COMPOUND: Grade LS124NTA

Silane Crosslinkable PE Compound suitable for Low Voltage Cable insulation with thickness 0.5 – 2.0 mm

Product Description

LS124NTA is Silane - XLPE compound produced under Monosil Technology (One – step process) for using in manufacture of power cable insulation. **LS124NTA** is Silane grafted polyethylene with additives and processing aids.

Typical Applications

LS124NTA is for low voltage wire and cable insulation.

LS124NTA is natural color.

Specification

The property requirement of the following material specifications

IEC 60502-1

Standard Package

Standard Package of **LS124NTA** is 25 kgs in vacuum sealed aluminium bag and is in outer kraft paper bag.

Physical Properties

Property	Test method	Spec.	Value	Unit
Melt Flow Index, Base Resin (190 °C, 2.16 kg)	ASTM D-1238	>2.5	2.8	g/10 min.
Density	ASTM D-1505	0.92±0.03	0.92	g/ cm ³
Elongation at Break	IEC 60811-1-1	Min. 200	>450	%
Tensile Strength	IEC 60811-1-1	Min 12.5	>18	MPa
After aging in oven (135 °C, 168 hours)				
Change of Elongation	IEC 60811-1-2	± 25	~-10	%
Change of Tensile Strength	IEC 60811-1-2	± 25	~-13	%
Hot set test (200 °C, 0.2 MPa, 15 min.)				
Elongation under load	IEC 60811-2-1	Max. 175	~-30	%
Elongation after cooling	IEC 60811-2-1	Max. 15	~-10	%



CHEMTECH COMPANY LIMITED

D_8A4_CN, My Phuoc 3 IP, Thoi Hoa, Ben Cat, Binh Duong, Vietnam

Tel: +84 2743 784 992 Fax: +84 2743 767 088

www.chemtechxlpe.com.vn

Issue date: January 1, 2024

TECHNICAL DATA SHEET

Crosslinkable Polyethylene Compound

XLPE – LS124NTA

Electrical Properties

Dielectric Strength	IEC 60243	>30	35	KV/mm
Dielectric Constant (50 Hz)	IEC 60250	<2.3	2.2	-
Volume Resistivity (1 kV)	IEC 60093	$>1.0 \times 10^{16}$	1.0×10^{17}	$\Omega \cdot \text{cm}$
Gel content	ASTMD 2765	>70	85	%

Processing Guidelines

- Extrude for cable insulation with guideline processing condition as below:
- Extruder type: General extruder design for processing Polyethylene
- L/D ratio of screw: L/D 26 – 30
- Compression ratio: 2:1 to 3:1
- Processing condition

Zone 1 (°C)	Zone 2 (°C)	Zone 3 (°C)	Zone 4 (°C)	Head (°C)	Die (°C)
150 -160	160 -170	170 - 180	180 -190	190 - 200	220 -250

This profile will vary slightly depending on extruder type, head design and output

1. Guideline Curing time

Thickness (mm)	Immerse in hot water 90 °C (Hours)	Ambient cure at 30°C, 80% RH (days)
1	1	2
2	4	8

Note: Specimens are made by strip passed to roller with 1mm and 2mm, immersed in hot water 90 °C then take sample in the middle part of the specimen.

2. It is recommended:

- Use all material after open the aluminum packaging within 2 – 3 hours.
- Screen mesh 40-60 is recommended.
- **Do not** dry grafted polyethylene.
- When change size of cable, should clean machine before run next cable.



CHEMTECH COMPANY LIMITED

D_8A4_CN, My Phuoc 3 IP, Thoi Hoa, Ben Cat, Binh Duong, Vietnam
 Tel: +84 2743 784 992 Fax: +84 2743 767 088
 www.chemtechxlpe.com.vn

Issue date: January 1, 2024

TECHNICAL DATA SHEET
Crosslinkable Polyethylene Compound

XLPE – LS124NTA

Storage

The shelf life of the products 12 months from the date of production, intact bags should be stored in ambient temperature (30 – 35 °C), in dry and dust free location. Avoid storage outside, water vapor absorbed. Avoid exposure to sunlight during storage.

Safety

The product is not classified as a dangerous and is intended for industrial use only. Please see our “Safety Data Sheet” for details.

Disposal

Disposal must be specially treated adhering to official regulations.

Related Documents

Safety Data Sheet, Handling and Storage Manual.

Disclaimer

- The product can be used only for the application as specified here above.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatever for the accuracy and completeness of such information.
- We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability of fitness for a particular purpose.
- It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.
- No ability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

